

# MATERIAL INFORMATION SHEET

DATE: 10/01/02

POLYETHYLENE ROTATIONAL MOLDING RESIN

MATERIAL TYPE: CS 9354U COLORS

UTILITY MOLDING COMPOUND

<u>PROPERTIES</u>	<u>ASTM</u>	<u>ENGLISH UNIT</u> (MINIMUM VALUES)
MELT INDEX	D-1238	4.0 g/10 min.
DENSITY	D-1505	.935 g/cc
TENSILE STRENGTH @ YIELD .125" THICKNESS	D-638	2500 psi
FLEXURAL MODULUS @ 1% STRAIN	D-790	85,000 psi
LOW TEMP. IMPACT .125" SPECIMEN	ARM Method	50 ft-lbs.

#### FOR YOUR PROTECTION

The information and recommendations in this publication are to the best of our knowledge are reliable. Suggestions concerning uses or applications are only the opinion of JERICO PLASTIC INDUSTRIES, INC. and users should make their own tests to determine the suitability of this product for their own particular purposes. However, because of numerous factors affecting results, JERICO PLASTIC INDUSTRIES, INC. makes no warranty of any kind, expressed or implied. Including those of merchantability and fitness for purpose other than the material conforms to its applicable current standard specifications. Statements herein should not be construed as representations of warranties. The responsibility of JERICO PLASTIC INDUSTRIES, INC. for claims arising out of breach warranty, negligence, strict liability, or otherwise is limited to the purchase price of the material.

# JERICO PLASTIC IND. INC.